

产品类别 Product Category	牌号Grade	测试标准、测试项目 Test criteria, test items							特性及用途 Property and Application
		熔指 MFI g/10min(230℃, 2.16kg)	密度 Density g/cm³	拉伸强度 Tensile Strength MPa	弯曲强度 Flexural Strength Mpa	弯曲模量 Flexural modulus Mpa	悬臂梁缺口冲击强度 Notched Izod impact strength J/m	热变形温度HDT (0.45MPa) °C	
		ASTM D1238	ASTM D792	ASTM D638	ASTM D790		ASTM D256	ASTM D648	
耐候PP Weather resistant pp	UR-2025	10	1.09	33	49	2400	29	130	高刚性, 户外制件 High rigidity, outdoor parts
	UR-2020	10	1.04	30	40	2000	32	120	高刚性, 户外制件 High rigidity, outdoor parts
	UR-2030	10	1.13	20	35	1900	55	120	高冲击, 户外制件 High impact, outdoor parts